

PLASTOFLEX 71

Frost-protecting wax for fruit trees

Property and Unit	Requirement	Method
Viscosity at 100 °C, mm ² /s	10-13	MSZ EN ISO 3104
Congealing point (rotational), °C	64-68	MSZ 11726
Drop melting point, °C	70-74	ASTM D 127
Penetration at 25 °C, 0,1 mm, min.	70	MSZ 15972
Flash point (CL), °C, min.	250	ASTM D 92

PRODUCER and EXPORTER

Production plant:
BOGDÁNY PETROL Ltd.
H-4511 Nyírbogdány
Gyártelep
HUNGARY
Phone: +36-42/232-377
Fax: +36-42/232-227

Export Sales Office:
BOGDANY PETROL Ltd.
H-1117 Budapest
Fehérvári út 84/A.
HUNGARY
Phone: +36-1/324-2101
Fax: +36-1/324-2102
Email: export@bogdanypetrol.hu



ISO 9001 – ISO 14001